

PRODUCT

Two component Epoxy Finishing a WRAS, UK, approved product.

PROPERTIES

- ❖ Glossy Enamel.
- ❖ Protective & higher degree of non-permeable properties.
- ❖ Excellent toughness & adhesion to substrate.
- ❖ Excellent resistant to water.

TYPICAL USES

- ❖ Pipe lines.
- ❖ Marine & Industrial atmosphere.
- ❖ Chemical Plants, Oil Refineries.
- ❖ Pharmaceuticals, Fertilizer Plants, Paper Mills.
- ❖ Food Processing Units etc.

SURFACE PREPARATION

Degrease and blast clean to SA 2½ grade minimum of Swedish specification SIS-05-5900-1967. Surface profile should not exceed 65 microns.

If blast cleaning is not possible, follow manual/mechanical cleaning to St2 or St3 grade minimum.

Surface should be clean, dry, free from oil, grease, salt and other surface contaminants before applying EDELPOXY FN 132.

STORAGE LIFE

Upto 9 months so long as the material stored in a sealed container.

PRECAUTIONS

Not to be applied when the temperature is above 50°C and relative humidity rises above 90%.

Mixed paint should be used off within stipulated pot life.

For proper curing of film, ambient temperature should not be lower than 10°C and adequate ventilation should be provided during application.

The information given in this data sheet is true to the best of our knowledge, observed while tested in ideal condition in our laboratory.

TYPE

Two pack system.

MIXING RATIO

Base : Hardener = 3 : 1 / Vol.

POT LIFE

1½ to 2¼ hours after mixing base & hardener.

METHOD OF APPLICATION

Brush / Roller / Spray.
(Airless Spray recommended for uniform and high film build).

NOTES ON AIRLESS SPRAY

Tip range : 15 - 21 thou.
Total output fluid pressure : 1500 - 2500 p.s.i. (106 - 176 kg / cm²).

RECOMMENDED D.F.T.

70 ± 10 µ per coat.

CORRESPONDING W.F.T.

150 - 200 µ approx.

THEORETICAL SPREADING RATE

6.7 - 5.0 m² / ltr. / coat.

DRYING TIME

Touch dry : 25 minutes.
Surface dry : 1¼ hours.
Handleable dry : 2 hrs.
Full cure : 7 days.

FINISH

Glossy.

COLOUR

Blue, Green, Bright Red, Brown Red & other selected shades.

INTERVAL BEFORE OVERCOATING

Minimum : 12 hrs.
Maximum : 7 days.

FLASH POINT

Above 20°C.

SHELF LIFE

Nine months from the date of manufacture for an airtight & properly sealed container.

THINNER

May be used PCC Epoxy Thinner, if necessary.

SAFETY PRECAUTIONS

Please see Health & Safety Data Sheet.

GENERAL INFORMATION

- A). Drying time and overcoating time will vary with (a) film thickness (b) humidity (c) temperature (d) ventilation and natural or artificial air movement. The ventilation is essential specially in potable situations.
- B). It is also to be noted that hard dry time is arbitrary and does not mean complete evaporation of solvent and it is imperative that the solvents are completely evaporated.

NOTE

For adverse and drastic climatic and corrosive atmospheric conditions, suitable anticorrosive and protective primer or primer surfacer may be coated before application of EDELPOXY FN 132.

P C CHANDA & COMPANY (P) LIMITED

RAVI AUTO HOUSE

103, PARK STREET, KOLKATA 700 016.INDIA.

PHONE : +91(033) 2227-2525, 2227-2526

FAX : +91(033) 2227-2528

e-mail : chandapaints@vsnl.net